



J. M. Engineering Co.

A collage of images related to engineering and manufacturing, including a blue and white airplane, various colored heat shrink sleeves, rolls of yellow and green sleeves, a circuit board, and wind turbines. A yellow square is positioned behind the 'PRODUCTS' text.

PRODUCTS

A light gray world map is visible in the background of the central section.

Heat Shrink Sleeves

Single Wall Heat Shrink Sleeves



Visit Us

Manhar Bldg., 3rd Floor, 177,
Lohar Chawl, Mumbai –
400002, Maharashtra (INDIA)



Email Us

info@jmenggco.in



Call Us

T: +91-22-2206 1671
F: +91-22-2209 0291



RSFR-H

Universal heat shrink tubing with excellent physical and mechanical properties



Features

- Flexible
- Flame retardant
- Continuous operating temperature: -55 ~ 125
- Fully shrink temperature: 125
- RoHS compliant

Dimensions

Size		As Supplied	After Recovery		Standard Package
Inch	mm	Internal Diameter mm	Internal Diameter mm	Wall Thickness mm	Spool Length M/spool
3/64	0.8	1.1±0.2	0.50	0.22	200
1/16	1.0	1.5±0.2	0.65	0.28	200
	1.5	2.0±0.2	0.85	0.32	200
3/32	2.0	2.5±0.2	1.00	0.35	200
	2.5	3.0±0.2	1.30	0.38	200
1/8	3.0	3.5±0.2	1.50	0.40	200
	3.5	4.0±0.2	1.80	0.42	200
	4.0	4.5±0.2	2.00	0.45	200
3/16	4.5	5.0±0.2	2.30	0.50	200
	5.0	5.5±0.2	2.5	0.55	100
1/4	6.0	6.5±0.2	3.0	0.55	100
5/16	7.0	7.5±0.3	3.5	0.55	100
	8.0	8.5±0.3	4.0	0.60	100
3/8	9.0	9.5±0.3	4.5	0.60	100
	10.0	10.5±0.3	5.0	0.60	100
	11.0	11.5±0.3	5.5	0.60	100
1/2	12.0	12.5±0.3	6.0	0.60	100
	13.0	13.5±0.3	6.5	0.65	100
	14.0	14.5±0.3	7.0	0.65	100
5/8	15.0	15.5±0.4	7.5	0.70	100
	16.0	16.5±0.4	8.0	0.70	100
	17.0	17.5±0.4	8.5	0.70	100
3/4	18.0	19.0±0.5	9.0	0.80	100
	20.0	21.0±0.5	10.0	0.80	100
	22.0	23.0±0.5	11.0	0.80	100
1	25.0	26.0±0.5	12.5	0.90	50
	28.0	29.0±0.5	14.0	0.90	50
1-1/4	30.0	31.5±1.0	15.0	0.95	50
1-1/2	35.0	36.5±1.0	17.5	1.00	50
	40.0	41.5±1.0	20.0	1.00	50
	45.0	46.5±1.0	22.5	1.00	25
2	50.0	50	25.0	1.00	25
	60.0	60	31.0	1.30	25
	70.0	70	36.0	1.30	25
3	80.0	80	41.0	1.46	25
	90.0	90	46.0	1.46	25
4	100.0	100	51.0	1.46	25
5	120.0	120	61	1.56	25
6	150.0	150	76	1.56	25
7	180.0	180	91	1.56	25

Technical Data

Property	Test Method	Typical Performance
Tensile strength(MPa)	ASTM D 2671	10.4
Ultimate elongation(%)	ASTM D 2671	200
Tensile strength after heat aged(Mpa)	158 X168h	7.3
Ultimate elongation after heat aged (%)	158 X168h	100
Longitudinal change(%)	ASTM D 2671	-5%~+5%
Flammability	ASTM D 2671 C method	VW-1
Voltage withstand	UL 224, 2500V, 60s	No breakdown
Dielectric strength (kV/mm)	ASTM D 149	15
Volume resistivity (Ω·cm)	ASTM D 876	10 ¹⁴